



# Teflon™ PTFE

## Fluoropolymer Resins

### Teflon™ PTFE Fluoropolymer Resins at a Glance

## Product Information

Products made with Teflon™ fluoropolymer resins have exceptional resistance to high temperature, chemical reaction, corrosion, and stress-cracking.

The mechanical toughness, electrical, and low-friction properties of Teflon™ PTFE make it the preferred plastic for a host of applications and processing techniques.

### Typical Properties of Teflon™ PTFE Granular Molding Powders<sup>1,2</sup>

Resin Type	Resin <sup>3</sup>	Average Particle Size (µm)	Bulk Density (g/L)	Standard Specific Gravity	Tensile Strength (MPa [psi])	Elongation at Break (%)	Initial Melting Peak Temperature (°C)	Second Melting Peak Temperature (°C)	Thermal Instability Index	Water Content (%)	Select Features <sup>4</sup>
Teflon™ PTFE Granular	7A X	38	460	2.16	48.3 [7000]	375	344 ± 10	327 ± 10	3	<0.04	Designed to be molded into shapes for skived films and sheets, gaskets, packings, mechanical seals, and similar products
	7C X	31	260	2.16	39.3 [5700]	350	342 ± 10	327 ± 10	3	<0.04	Used in applications where excellent flex life is required
	8A X	490	680	2.15	41.4 [6000]	330	342 ± 10	327 ± 10	8	<0.04	Resin designed for low preform pressure that allows for shallow molds and improved surface smoothness
	807N X	550	900	2.16	33.0 [4786]	320	344 ± 10	327 ± 10	5	<0.04	Multi-purpose resin that yields high productivity, due to its high fill density
	NXT 70	33	400	2.17	38.6 [5600]	550	N/A	327 ± 10	N/A	N/A	Modified PTFE designed for compression molding
	NXT 75	33	400	2.17	41.4 [6000]	600	N/A	327 ± 10	N/A	N/A	Modified PTFE designed for compression molding with improved weldability
	NXT 85	550	700	2.17	27.6 [4000]	450	N/A	327 ± 10	N/A	N/A	Pelletized version of the NXT75 product

Typical Properties of Teflon™ PTFE Fine Powders<sup>1,2</sup>

Resin Type	Resin <sup>3</sup>	Average Particle Size (µm)	Bulk Density (g/L)	Standard Specific Gravity	Thermal Instability Index	Extrusion Pressure (MPa [psi])	Initial Melting Peak Temperature (°C)	Second Melting Peak Temperature (°C)	Reduction Ratio Range	Select Features <sup>4</sup>
Teflon™ PTFE Fine Powder	6C X	475	490	2.176	<50	53.0 [7700] at 1600:1	344	327 ± 10	250–2000	Designed for processing at medium to high reduction ratios (250–2000). Particularly suitable for production of wire coating, wire jacketing, and tubing at fast sintering rates
	6CN X	400	470	2.185	<50	50.0 [7252] at 1600:1	341	327 ± 10	250–2000	Designed for processing at medium to high reduction ratios. Particularly suitable for production of wire coating, wire jacketing, and tubing at fast sintering rates
	60 X	500	500	2.185	<50	8.0 [1160] at 100:1	342	327 ± 10	10–300	Designed to facilitate the production of high-quality, low-density tape and beading
	62 X	480	495	2.152	<7	23.0 [3335] at 400:1	341	327 ± 10	100–600	Increased thermal stability, superior flex life, superior stress crack resistance, low permeability, and high clarity compared with other grades of PTFE fine powder
	62N X	480	495	2.148	<7	24.0 [3500] at 400:1	341	327 ± 10	100–600	Increased thermal stability, superior flex life, superior stress crack resistance, low permeability, and high clarity compared with other grades of PTFE fine powder
	62XT X	370	470	2.155	<7	38.5 [5584] at 1600:1	341	327 ± 10	400–1600	Increased thermal stability, superior flex life, superior stress crack resistance, low permeability, and high clarity compared with other grades of PTFE fine powder, as well as higher reduction ratios of 400–1600
	601 X	500	550	2.160	<50	9.0 [1300] at 100:1	342	327 ± 10	10–300	High molecular weight resin for unsintered stretched products and sintered products with high mechanical properties. Examples include small pore size filter membranes and gaskets
	602 X	550	550	2.172	<50	6.9 [1000] at 100:1	342	327 ± 10	10–300	Medium molecular weight resin for unsintered stretched products and sintered products with high mechanical properties. Applications include membrane applications with higher pore size and pipe liners
	605XT X	675	555	2.163	N/A	7.0 [1015] at 100:1	344	327 ± 10	10–300	Resin for unsintered stretched products and sintered products with high mechanical properties. Applications include membranes and pipe liners
	613A X	500	440	2.153	<50	27.6 [4000] at 100:1	342	327 ± 10	10–300	Designed for high-quality, low-density tape and beading
	640XT X	450	500	2.159	≤15	22.0 [3190] at 1600:1	344	327 ± 10	250–5000	High reduction ratio material for wire, cable, and tubing applications
	641XT X	400	475	2.166	<25	46.0 [6,670] at 2500:1	344	327 ± 10	250–5000	High reduction ratio material with increased extrusion line speed for wire, cable, and tubing applications
	650XT X	500	550	2.163	<20	8.8 [1276] at 100:1	344	327 ± 10	10–400	Resin for unsintered mono-axial and multidirectional stretched products and sintered products with high mechanical properties. Applications include membranes and gaskets
	669 X	450	520	2.167	N/A	7.5 [1090] at 100:1	344	327 ± 10	10–500	Designed for production of pipe liners and general tubing
	669N X	425	545	2.170	N/A	7.5 [1090] at 100:1	344	327 ± 10	10–500	Designed for production of pipe liners and general tubing
CFP 6000 X	500	460	2.183	<15	41.4 [6000] at 1600:1	342	327 ± 10	250–3000	Designed for wire coating, wire jacketing, and thin wall tubing	

## Typical Properties of Teflon™ PTFE Aqueous Dispersions<sup>1, 2</sup>

Resin Type	Resin <sup>3</sup>	Solids Content (% PTFE by Weight)	Density of Dispersion (at 60% Solids) (g/cm <sup>3</sup> )	Surfactant Content on PTFE Solids (%)	Dispersion Particle Size (µm)	pH of Dispersion	Brookfield Viscosity at 25 °C (MPa·s)	Continuous Use Temperature (°C)	Select Features <sup>4</sup>
Teflon™ PTFE Dispersion	DISP 30	60	1.51	6	0.220	10	25	260	General-purpose dispersion; preferred for coating and impregnating woven goods
	DISP 33	61	1.52	6.5	0.220	10	25	260	Formulated to provide void-free coatings and enhanced surface smoothness, adhesion, gloss, and weldability
	DISP 35	35	1.25	2.2	0.245	10	25	260	Used for co-coagulation with various fillers to produce products with range of strengths, porosities, and colors
	DISP 40	60	1.51	6	0.230	10	25	260	Enhanced shear stability; can be used in coating and additive applications
	DISP 50	60	1.51	6	0.200	10	25	260	Improved tensile strength for cast film applications

<sup>1</sup> See product information sheets for ASTM/ISO test methods.

<sup>2</sup> Typical properties are not suitable for specification purposes. The User is responsible for evaluating and determining whether this Chemours product is suitable and appropriate for a particular use and intended application. The conditions of evaluation, selection, and use of the Chemours product can vary widely and affect the use and intended application of the Chemours product. Because many of these conditions are uniquely within the User's knowledge and control, User must evaluate and determine whether the Chemours product is suitable and appropriate for a particular use and intended application.

<sup>3</sup> For inventory control purposes, product name may be followed by an X. Products labeled with or without an X following the grade name are equivalent, and all information in this document is applicable to both.

<sup>4</sup> See individual product information sheets for additional information.

## HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoropolymer resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit [www.teflon.com/license](http://www.teflon.com/license)

**CAUTION:** Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit [teflon.com/industrial](http://teflon.com/industrial)

For sales and technical support contacts, visit [teflon.com/industrialglobalsupport](http://teflon.com/industrialglobalsupport)

© 2024 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.